

A.H. Harris & Sons, Inc.<sup>®</sup>



CONSTRUCTION SPECIALTIES

Since 1916

## SUPER KURSEAL 30

ACRYLIC CONCRETE CURING AND SEALING COMPOUND

ASTM C-1315 • HIGH GLOSS • COST EFFECTIVE

VOC Content: 625 gr./liter or 5.22#/gal – Cure & Seal

### DESCRIPTION

**SUPER KURSEAL 30** a high gloss product, is a 100% styrene acrylic copolymer based curing, sealing, hardening, dustproofing and water repellent compound. When applied, it quickly dries to a hard clear high gloss coating that is tough, resistant to yellowing and many chemicals and long lasting. The product is ideal for use on floors, walls, architectural sections and as a base coat for a variety of top coatings. Super Kurseal 30 forms a clear film that provides superior shine that enhances the appearance of architectural concrete. Super Kurseal 30 features breathable technology which allows moisture vapor to pass through rather than becoming trapped, preventing whitening, peeling and flaking. Super Kurseal 30 is formulated from customized styrene acrylic resins manufactured especially for use on cementitious surfaces. The formulation contains no modifiers or extenders that can cause cure and seal to yellow, blush or look non-glossy Super Kurseal 30 provides an excellent base for most adhesives, paints and a variety of topcoats. These products meet the requirements of the Tile Adhesion Test of the Resilient Tile Institute and the Tile Adhesion Test Requirements of ASTM-C-1315.

### BENEFITS

- Provides for complete development of concrete's wear resistance and strength properties
- High Gloss
- Apply to damp surfaces without whitening or loss of adhesion
- Seals and hardens surface reducing clean up and maintenance
- Can be applied to 20<sup>0</sup>F.
- Excellent protection against staining, attack by alkali, oil, salt, cleaners and common industrial chemicals
- Prevents efflorescence, dusting and spalling
- Breathable technology
- Excellent base for adhesives
- Re-coatable

### APPLICATION

- Product is supplied at the proper consistency for application and dilution will reduce efficiency and gloss.
- Thoroughly mix before applying.
- To improve non-slip profile use **Certi-Vex<sup>®</sup> Grip**.
- Note; product forms a surface film quickly depending on temperature, humidity and wind conditions therefore, for best results follow all equipment and application instructions carefully.

### **If applying by sprayer:**

- Apply by low-pressure high solids commercial grade solvent resistant sprayer with neoprene fittings. (Do not use garden or form oil sprayers).
- The sprayer must be clean and dry. If cleaning with solvents is required, use **Certi-Vex<sup>®</sup> Equipment Cleaner**. Clean sprayer as directed between applications to ensure best results.
- If spraying and back rolling, best application is to spray enough material that a second person can immediately back roll following the spray applicator. Follow roller instructions below. Caution; do not delay the back roll as the area will dry quickly.

### **If applying by roller:**

- For best results use Vexcon's **EvenFlow Applicator** or ¼ " nap mohair roller.
- Use a roller pan to take off excess product. Do not dip and roll or pour and spread
- Do not over-work material, apply in a single lapping motion. Do not roll area back and forth, this can cause the film to break and product to become stringy.
- Do not run roller dry, keep a wet edge and do sections small enough to roll only once over wet material.
- Do not roll over dry material this can cause the product to become stringy. To aid in keeping roller wet and fluid, keep a roller pan filled with **Certi-Vex<sup>®</sup> Equipment Cleaner**.
- Over rolling or using incorrect rollers will cause bubbles to form in the coating. If this occurs on final coat corrective procedure is to apply a light coat of **Certi-Vex<sup>®</sup> Coating Repair** over the area. This will recast (heel) the coating and eliminate the bubbles. If this occurs on first coat, follow corrective procedure above then apply final coat.
- Material should not be allowed to puddle.
- Do not allow sealed area to become wet with water until dry. See dry times.
- Protect all surrounding areas from over spray.
- The sealer can be applied to damp surfaces, however, do not apply over puddled water.
- A uniform appearance requires even coats leaving no gaps. Some areas may be more porous than others; these areas may require additional coats to even out the appearance. Caution: Do not over-apply material. See special notes section.

## CURING AND SEALING NEW CONCRETE

- Apply Super Kurseal 30 to still damp freshly finished concrete as soon as the surface cannot be marred, and water sheen disappears. Do not apply over freestanding water.
- If application is delayed, concrete must be kept wet (preferably by water spray mist) until product can be applied.
- If concrete is allowed to dry use **Certi-Vex® Concrete Etch & Efflorescence Remover** to clean and prepare the surface.
- Apply first coat at 300 sq.ft./gal (7.5 m<sup>2</sup>/L). A second coat is recommended for long term durability. See Second Coat section.

## SURFACE PREPARATION EXISTING CONCRETE

The concrete surface must be properly repaired, structurally sound and cleaned. Use A.H. Harris surface prep and cleaning products to properly clean the surface prior to application.

- To remove coatings such as epoxy's, sealers and curing compounds use **Certi-Vex® Concrete Stripper**.
- The concrete should be cleaned with **Certi-Vex® Super Degreaser & Cleaner** to remove any dust, dirt or debris and allowed to dry for a minimum of 24 hours after cleaning.
- To remove efflorescence or to etch the surface for improved material penetration use **Certi-Vex® Etch & Efflorescence Remover**.
  - There should be no freestanding water.
- Large cracks should be repaired using **PowerCoat® Epoxy Joint Sealant**.

## SEALING EXISTING CONCRETE

- Prior to application a test area must be performed to determine proper application rate and required surface preparation.
- To determine that the concrete is penetrable perform a water absorbency test by applying water to a representative portion of the prepared concrete floor. A properly prepared surface when dry will immediately absorb clean water without any surface beading effects.
- If required use **Certi-Vex® Etch & Efflorescence Remover** to improve sealer penetration. Application to still damp surfaces is acceptable however free standing water must be removed.
- Apply Super Kurseal 30 at 400-500 sq.ft. /gal (10-12.5 m<sup>2</sup>/L) on hard non-porous floors and 250-300 sq.ft. /gal (6.2-7.5 m<sup>2</sup>/L) on porous floors.

## SECOND COAT

Apply after 1<sup>st</sup> coat has dried at 400-500 sq.ft. /gal (10-12.5 m<sup>2</sup>/L).

## TOPCOATS AND ADHESIVES

Super Kurseal 30 cured concrete can be topcoated with a variety of paint, adhesives and mastics, a minimum of 28 days after application. It is recommended that a test area be applied prior to coating the entire surface, since products can adhere to concrete in varying degrees. Check with the manufacturer of the topcoat for any precautionary and compatibility information.

## SPECIFICATIONS/COMPLIANCE

- ASTM C 1315 Type 1, Class B
- AASHTO M-148
- ASTM C 309 Type 1 Class A&B
- Meets ADA and ASTM D 2047 non-slip
- USDA approved
- Meets USEPA AIM VOC regulations
- Federal specification TTC0800A (GSA FSS) Type 1
- VOC: 625 gr./liter or 5.22#/gal – Cure & Seal

CSI #033900

## MAINTENANCE

Spills should be removed promptly and cleaned. Sealed areas should be cleaned regularly, use **Certi-Vex® Super Degreaser & Cleaner** for all cleaning requirements. Periodic reapplication may be required as the sealer wears off.

## SPECIAL NOTES

- To assist in application note, 200 sq.ft. /gal wet film is approximately equal to the thickness of a sheet of paper
- Will tend to show rubber burns or tire marks
- Will cause bleeding of bituminous surfaces
- May enhance mottling of colored surfaces
- Not gasoline resistant, use **PowerCoat® Epoxy** products
- Over application may lead to surface discoloration and improper sealer performance
- Do not apply more material per gallon than specified
- Can apply when surface temperatures are 40° F - 85° F, when below or above these ranges review Vexcon's Cold and Hot Weather Application Guides
- Shelf Life: If properly stored in its original sealed container, three years from date of manufacture. Rotate your stock.
- For use by experienced applicators
- Cert-Vex® and PowerCoat® are registered trademarks of Vexcon Chemicals. All rights reserved.

## PACKAGING

Super Kurseal 30 is available in 55-gallon drums and 5-gallon pails.

## VITAL STATISTICS

- Flash Point (TCC) 106° F (41°C)
- Boiling Point (706 mmHg) 310-403 F (154-207°C)
- Autoignition Temp Above 473° F (245°C)
- Extinguishing Media Foams, Dry Chemical, CO2, Water may be used to reduce the rate of burning and for cooling containers.

## PHYSICAL PROPERTIES & DRY TIMES

- |                  |             |                   |            |
|------------------|-------------|-------------------|------------|
| • Wet appearance | Water White | • Dry appearance  | Clear      |
| • Dry to touch   | 45 minutes  | • Dry - tack free | 85 minutes |
| • Foot traffic   | 24 hours    | • Vehicle traffic | 72 hours   |
| • Solids         | 30% minimum |                   |            |

Note: All calculations based upon 68-77° F (20-25° c).

Lower temperatures and relative humidity will extend dry times.

## HEALTH AND SAFETY

- Use only with adequate ventilation.
  - Use of gloves, goggles and other protective clothing is advised when using this product.
  - If swallowed, do not induce vomiting.
  - Use of respirators is advised when using in confined areas.
- A.H. Harris MSDS is an integral part of the safety and application of our product. A short synopsis is provided in this product data sheet. Before using this product obtain a copy of the MSDS from A.H. Harris.

## CONTACT US @

Additional product information, technical assistance and customer service is available by contacting A.H. Harris.

- [www.ahharris.com](http://www.ahharris.com)